

	ETI™ SC1 (Silicone)
	ETI™ FS173 (Matte Paper)
	ETI™ AD25 (Removable adhesive)

### Facestock

ETI™ FS173 is a one-side coated matte paper with a superior brightness.

<i>Caliper</i>	0,0033 in.	or 0,0083 cm ± 10%
<i>Basis weight</i>	0,018 lbs/ft <sup>2</sup>	or 90 g/m <sup>2</sup>
<i>Tensile strength TD</i>	18,84#/in.	or 3,3 kN/m
<i>Tensile strength MD</i>	34,26#/in.	or 6,0 kN/m
<i>Gloss</i>	25%	
<i>Opacity</i>	90%	
<i>Brightness</i>	91%	

### Adhesive

ETI™ AD25 is a removable and remoistenable adhesive. It has a fast remoistening tack and speed.

<i>Type</i>	Removable
<i>Application Temperatures</i>	275 to 350 °F or 150 to 175 °C
<i>Service Temperatures</i>	-5 to 175 °F or -20 to 80 °C

### Silicone

ETI™ SC1 is a silicone coating.

### Additional Information :

#### Printing and Converting

Printable directly on the facestock in all classical processes processes : flexographic, gravure, silk screen, UV letterpress processes. Excellent conversion characteristics in rotary and flat-bed.

#### Application and uses

This high quality multipurpose label is recommended for applications where clean removability is important.

#### Shelf Life

One year when stored at 72°F at 50% RH.

### Statement of practical use

As with all pressure-sensitive materials, this product should be tested thoroughly under end-use conditions to ensure it meets the requirements of the specific application.