



ETI™ FS180 (Wine Paper)  
 ETI™ AD24 (Removable adhesive)  
 ETI™ SC2 (Silicone)  
 ETI™ LN20 (SCK)

**Facestock**

ETI™ FS180 is a wine paper smooth on the verso and with pronounced laid lines on the recto.

<b>Caliper</b>	0,0043 in.	or 0,0110 cm ± 10%
	0,0048 in.	or 0,0122 cm ± 10%
<b>Grammage</b>	0,015 lbs/ft <sup>2</sup>	or 72 g/m <sup>2</sup>
	0,016 lbs/ft <sup>2</sup>	or 80 g/m <sup>2</sup>
	0,018 lbs/ft <sup>2</sup>	or 90 g/m <sup>2</sup>
<b>Colors</b>	2 whites	
	2 ivories	

**Adhesive**

ETI™ AD24 is an adhesive removable with warm and soapy water. It has a fast remoistening tack and speed.

<b>Type</b>	Removable	
<b>Application Temperatures</b>	275 to 350 °F	or 150 to 175 °C
<b>Service Temperatures</b>	-5 to 175 °F	or -20 to 80 °C

**Silicone**

ETI™ SC2 is a silicone coating enabling different release possibilities.

**Liner**

ETI™ LN20 is a supercalendered release base paper with a high

<b>Caliper</b>	0,0025 in.	or 0,0065 cm ± 10%
<b>Basis Weight</b>	0,0135lbs/ft <sup>2</sup>	or 65,84 g/m <sup>2</sup>
<b>Tensile Strenght TD</b>	25#/in.	or 43,8 N/cm ± 20%
<b>Tensile Strenght MD</b>	32#/in.	or 56,0 N/cm ± 20%
<b>Tear TD</b>	0,0062 lbs/ft <sup>2</sup>	or 30 g/m <sup>2</sup>
<b>Tear MD</b>	0,0064 lbs/ft <sup>2</sup>	or 31 g/m <sup>2</sup>

**Performance data**

**Peel Adhesion**

<b>Stainless steel</b>	1,5 lbs	or 0,68 kg
<b>HDPE</b>	1,0 lbs	or 0,45 kg
<b>Polypropylene</b>	1,0 lbs	or 0,45 kg
<b>Glass</b>	1,4 lbs	or 0,63 kg

**Loop Tack**

<b>Stainless steel</b>	0,9 lbs	or 0,41 kg
<b>HDPE</b>	1,5 lbs	or 0,68 kg
<b>Polypropylene</b>	1,7 lbs	or 0,77 kg
<b>Glass</b>	1,8 lbs	or 0,81kg

<b>Total Construction Caliper (approximate)</b>	0,0080 in. or 0,0200 cm ± 10% 0,0085 in. or 0,0215 cm ± 10%
---	--

<b>*3 possibilities of release</b>	High Medium Low
------------------------------------	-----------------------

**Additional Information :**

**Printing and Converting**

Printable directly on the facestock by flexography and offset. It is possible to diecut and to strip this product on standard web-fed presses with flatbed or rotary dies at high speeds. Dies tooled specifically for this construction are recommended for best performances.

**Application and uses**

This product is particularly recommended for wet or dry glass bottles, wet or dry plastic bottles, jars or metal tins. This product is designed for applications where clean removability is necessary.

**Shelf Life**

One year when stored at 72°F at 50% RH. Surface tension values may decrease in time.

**Statement of practical use**

As with all pressure-sensitive materials, this product should be tested thoroughly under end-use conditions to ensure it meets the requirements of the specific application.