

	ETI™ FS183 (Wine Paper)
	ETI™ AD25 (Removable adhesive)
	ETI™ SC2 (Silicone)
	ETI™ LN50 (SCK)

Facestock

ETI™ FS183 is a wine paper smooth on the verso and with soft "martele grain" on the recto.

Caliper	0,0046 in.	or 0,0118 cm ± 10%
Grammage	0,018 lbs/ft²	or 90 g/m²
Colors	White	

Adhesive

ETI™ AD25 is a removable and remoistenable adhesive. It has a fast remoistening tack and speed.

Type	Removable	
Application Temperatures	275 to 350 °F	or 150 to 175 °C
Service Temperatures	-5 to 175 °F	or -20 to 80 °C

Silicone

ETI™ SC1 is a silicone coating enabling different release possibilities.

Liner

ETI™ LN50 is a supercalendered paper.

Caliper	0,0022 in.	or 0,0056 cm ± 10%
Basis Weight	0,0133 lbs/ft²	or 62 g/m²
Tensile Strenght TD	20#/in.	or 13,8 N/cm ± 20%
Tensile Strenght MD	38#/in.	or 26,2 N/cm ± 20%
Opacity	60%	
Moisture Content	6,0%	

Performance data

Peel Adhesion

Stainless steel	1,4 lbs	or 0,63 kg
	0,9 lbs	or 0,41 kg
HDPE	0,8 lbs	or 0,38 kg
Glass	1,3 lbs	or 0,59 kg

Loop Tack

Stainless steel	1,6 lbs	or 0,72 kg
HDPE	1,0 lbs	or 0,45 kg
Polypropylene	0,8 lbs	or 0,38 kg
Glass	1,3 lbs	or 0,59 kg

Total Construction Caliper (approximate)	0,0075 in. or
	0,0190 cm ± 10%

*3 possibilities of release	High
	Medium
	Low

Additional Information :

Printing and Converting

Printable directly on the facestock by flexography and offset. It is possible to diecut and to strip this product on standard web-fed presses with flatbed or rotary dies at high speeds. Dies tooled specifically for this construction are recommended for best performances.

Application and uses

This general purpose product is recommended for applications where clean removability is important. This product is particularly recommended for wet or dry glass bottles, wet or dry plastic bottles, jars or metal tins.

Shelf Life

One year when stored at 72°F at 50% RH. Surface tension values may decrease in time.

Statement of practical use

As with all pressure-sensitive materials, this product should be tested thoroughly under end-use conditions to ensure it meets the requirements of the specific application.